





## sophisticated style

For a subtle approach to cosmetic styling, turn to SunSHINE® Soft Effects. This ultrafine synthetic mica pearl portfolio (INCI designation Synthetic Fluorophlogopite) strikes a unique balance between light transmittance and reflection to deliver a radiant look while minimizing the appearance of surface imperfections. With no end-use restrictions, their soft texture enhances skin feel in virtually any application. And with market-leading purity levels, SunSHINE Soft Effects delivers quality that is unmistakably SunSHINE.

SunSHINE Soft Effects	Product Code	Particle Size Distribution	Chemical Composition %		
			Synthetic Fluorophlogopite	TiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>
Soft White	C80-4000	2-16 microns	59-70	30-41	
Soft Gold	C81-4010	2-13 microns	37-48	52-63	
Soft Red	C81-4030	2-13 microns	31-42	58-69	
Soft Violet	C81-4040	2-13 microns	27-38	62-73	
Soft Blue	C81-4050	2-13 microns	25-36	64-75	
Soft Green	C81-4060	2-13 microns	18-29	71-82	
Soft Golden	C84-4011	2-13 microns	33-48	49-60	3-7
Soft Bronze	C84-6080	2-13 microns	46-56		44-54
Soft Copper	C84-6090	2-13 microns	39-49		51-61
Soft Russet	C84-6070	2-13 microns	35-45		55-65

	Heavy Metal Specifications									
	Hg	As	Pb	Cd	Ba	Sb	Cu	Cr	Ni	Zn
SunSHINE Soft White & Iridescent Effects	1 ppm	1 ppm	1 ppm	1 ppm	10 ppm	1 ppm	10 ppm	10 ppm	10 ppm	10 ppm
TiO <sub>2</sub> + Fe <sub>2</sub> O <sub>3</sub> coated SunSHINE Soft Metallic Effects	1 ppm	1 ppm	3 ppm	1 ppm	30 ppm	1 ppm	30 ppm	30 ppm	50 ppm	40 ppm
Fe <sub>2</sub> O <sub>3</sub> coated SunSHINE Soft Metallic Effects	1 ppm	1 ppm	3 ppm	1 ppm	30 ppm	1 ppm	30 ppm	30 ppm	60 ppm	60 ppm





C80-4000  
Soft White  
2-16 microns



C81-4010  
Soft Gold  
2-13 microns




C81-4030  
Soft Red  
2-13 microns




C81-4040  
Soft Violet  
2-13 microns




C81-4050  
Soft Blue  
2-13 microns




C81-4060  
Soft Green  
2-13 microns




C84-4011  
Soft Golden  
2-13 microns



C84-6080  
Soft Bronze  
2-13 microns



C84-6090  
Soft Copper  
2-13 microns



C84-6070  
Soft Russet  
2-13 microns

Although the information presented here is believed to be reliable, Sun Chemical Corporation makes no representation or guarantee to its accuracy, completeness or reliability of the information. All recommendations and suggestions are made without guarantee, since the conditions of use are beyond our control. There is no implied warranty of merchantability or fitness for purpose of the product or products described herein. In no event shall Sun Chemical Corporation be liable for damages of any nature arising out of the use or reliance upon the information. Sun Chemical Corporation expressly disclaims that the use of any material referenced herein, either alone or in combination with other materials, shall be free of rightful claim of any third party including a claim of infringement. The observance of all legal regulations and patents is the responsibility of the user.

SUNSHINE and SUNCHEMICAL are trademarks of Sun Chemical Corporation, registered in the United States of America and other countries.

Sun Chemical Performance Pigments  
General Sales Office USA  
International Operations Belgium  
Sun Chemical México  
www.sunchemical.com

+1 800 543 2323 ext. 287  
+32 1023 1500  
+52 55 5358 7247

**SunChemical®**  
a member of the DIC group 

HL 1/14 PMT-0017A